

**KANSAS DEPARTMENT OF TRANSPORTATION
 SPECIAL PROVISION TO THE
 STANDARD SPECIFICATIONS, 2015 EDITION**

SECTION 1110

AGGREGATES FOR SUBGRADE MODIFICATION OR RECONSTRUCTION

Page 1100-28, subsection 1110.2c.(1). Delete TABLE 1110-1 and replace with the following:

TABLE 1110-1: GRADING AND PLASTICITY REQUIREMENTS									
Type	Material	Percent Retained-Square Mesh Sieves¹							Plasticity Index
		1 1/2"	1"	3/4"	3/8"	No. 4	No. 16	No. 50	
SR-1	Crushed Stone	0	0-15			35-100		90-100	0-6
SR-3	Crushed Stone Screenings ³	0			0-5				0-5
SR-4	Sand-Gravel ⁴		0	0-5	0-20				0-6
SR-7	Sand-Gravel	0					5-50	85-100	0-6

¹All percent retained values shall be determined using the cumulative dry mass sum of the material retained on each sieve divided by the total dry mass of the material retained on the 200 sieve after washing and sieving (KT-2) and removal of all deleterious substances.

²This requirement does not apply if there is more than 70% retained on the No. 30 sieve.

³Do not exceed 7% of moisture contained in the aggregate when delivered to the road.

⁴Grading Factor is between 4.00-5.00.

Page 1100-28, subsection 1110.2c.(2). Add the following bullet point:

- Material passing No. 200 sieve (KT-2)15.0

Page 1100-28, subsection 1110.2c.(2). Add the following paragraph:

For limestone or sandstone screenings:

- Material passing No. 200 sieve (KT-2)15.0