

**KANSAS DEPARTMENT OF TRANSPORTATION
 SPECIAL PROVISION TO THE
 STANDARD SPECIFICATIONS, 2015 EDITION**

SECTION 1111

AGGREGATES FOR SURFACING OR RESURFACING

Page 1100-30, subsection 1111.2c.(1). Delete TABLE 1111-1 and replace with the following:

TABLE 1111-1: GRADING REQUIREMENTS FOR AGGREGATES FOR SURFACING OR RESURFACING								
Type	Material	Percent retained-square mesh sieve ¹						Fineness Modulus
		1 1/2"	1"	3/4"	3/8"	No. 8	No. 30	
SA-1	Sand-gravel		0	0-5	0-20			4.00 min.*
SA-2	Sand-gravel	0	1-15					5.00 min.
SA-6	Crushed Stone	0	0-5	5-25	45-100		95-100	
SA-7	Crushed Stone	0		25-50		85-100		
SA-X	Crushed Stone		0	0-5	35-65		95-100	

¹All percent retained values shall be determined using the cumulative dry mass sum of the material retained on each sieve divided by the total dry mass of the material retained on the 200 sieve after washing and sieving (KT-2) and removal of all deleterious substances.

*For fineness modulus less than 4.00 but greater than 3.75, provide additional materials as a penalty at a rate of 1.5% for each 0.05 less than 4.00 fineness modulus. Use a maximum lot size of 500 cubic yards or tons to determine penalty. Average all tests within the lot to determine penalty.

Page 1100-30, subsection 1111.2c.(2). Add the following:

- Material passing No. 200 sieve (KT-2) 3.0

05-11-15 C&M (KHL)
 Jul-15 Letting